

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
30 October 2003 (30.10.2003)

PCT

(10) International Publication Number
WO 03/089215 A1

(51) International Patent Classification⁷: **B29C 33/40**,
45/00

(21) International Application Number: PCT/US03/10219

(22) International Filing Date: 4 April 2003 (04.04.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/373,236 17 April 2002 (17.04.2002) US

(71) Applicant: STRATASYS, INC. [US/US]; 14950 Martin
Drive, Eden Prairie, MN 55344-2020 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): CRUMP, Steven,
Scott [US/US]; c/o STRATASYS, INC., 14950 Martin

Drive, Eden Prairie, MN 55344-2020 (US). **PRIEDE-**
MAN, JR., William, R. [US/US]; c/o STRATASYS, INC.,
14950 Martin Drive, Eden Prairie, MN 55344-2020 (US).


(74) Agents: **CHAPMAN, Gena, M.** et al.; **KINNEY &**
LANGE, PA, Kinney & Lange Building, 312 South Third
Street, Minneapolis, MN 55415-1002 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD,
SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,

[Continued on next page]

(54) Title: LAYERED DEPOSITION BRIDGE TOOLING



(57) Abstract: Disclosed is a method for making a prototype plastic injection molded part from a mold tool (10) built by fused deposition modeling. The mold tool (10) is built by depositing roads of a molten thermoplastic resin in layers in a predetermined pattern defined by computer file data representing the inverse of the desired prototype molded part, and is used in an injection molding machine without the addition of any reinforcement fill material or layers to create the prototype part. The disclosed method provides prototype plastic injection molded parts within a twenty-four hour time period.

WO 03/089215 A1